



Part Number: **T37-52**

Revision 20190524 - Generated 2019-May-30



OD	(nom. - bare core) (max. - after coating)	9.53 mm 9.91 mm	0.375 in 0.390 in
ID	(nom. - bare core) (min. - after coating)	5.21 mm 4.83 mm	0.205 in 0.190 in
Ht	(nom. - bare core) (max. - after coating)	3.25 mm 3.76 mm	0.128 in 0.148 in
Mass	(approximate)	1.0 grams	
Magnetic Dimensions	A_e - Eff. Mag. Cross Section L_e - Eff. Mag. Path Length V_e - Eff. Core Volume W_A - Min. Eff. Window Area s_a - Surface Area mlt - mean length per turn	0.0640 cm ² 2.31 cm 0.147 cm ³ 0.183 cm ² 3.47 cm ² 1.50 cm	
Inductance	μ_i (reference) A_L value (nominal) Test Winding Frequency Voltage on Agilent 4284A A_L tolerance	75 26 nH/N ² N=50, #30 AWG 10 kHz 0.014 V ±10%	
Core Loss	Core Loss(mW/cm ³)= $\frac{f}{\frac{a}{Bpk^3} + \frac{b}{Bpk^{2.3}} + \frac{c}{Bpk^{1.65}}} + d \cdot Bpk^2 \cdot f^2$ where B_{pk} expressed in gauss, f expressed in hertz, and: $a=1.00E+09$, $b=1.10E+08$, $c=2.10E+06$, $d=6.90E-14$	Bpk frequency Core Loss (nominal) Core Loss (maximum)	140 G 100 kHz 58 mW/cm ³ 67 mW/cm ³
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$ where H expressed in oersteds, and: $a=1.00E-02$, $b=4.66E-06$, $c=1.84$, $d=0.00$	H_{DC} Percent Initial Perm(nom.) Percent Initial Perm(min.)	50 Oe 61.6% 53.4%
Coating/Pkg	Coating Type: Voltage Breakdown (min.) Limit Package Quantity	Green/Blue Epoxy Paint 500 Vrms, 60Hz 3 mA, 5 s 20,000 Pcs/Box	

Winding Table	Wire Size	AWG	20	22	24	26	28	30	32	34	36	38	40
		mm	0.800	0.630	0.500	0.400	0.315	0.250	0.200	0.160	0.125	0.100	0.080
	Single Layer	Turns	12	16	21	26	34	42	53	67	84	105	132
	Full Winding	Rdc(Ω)	6.0 m	12.7 m	26.5 m	52.2 m	108.6 m	213.4 m	428.3 m	861.2 m	1.7	3.4	6.8
	Turns	13	20	32	49	76	117	181	280	433	671	1,038	
	Rdc(Ω)	6.5 m	15.9 m	40.4 m	98.4 m	242.8 m	594.5 m	1.5	3.6	8.9	21.8	53.7	

